

Typical Properties of Durafoam™ DK4141

Polymer	Neoprene/EPDM		
ASTM D1056 Classification	2C4		
ASTM D1056 Suffix Compliances	B2, C1, F1, M		
ASTM D6576 Classification	Type II A,B Medium/Firm		
Physical Property	Test Method	Result (US Units)	Result (Metric Units)
Density	ASTM D1056	8 – 13 pcf	128.1 – 208.2 kg/m ³
Compression Deflection 25%	ASTM D1056	13 – 17 psi	89.6– 117.2 kPa
Compression Set 50%	ASTM D1056	25% Max	25% Max
Water Absorption	ASTM D1056	5% Max	5% Max
Tensile Strength	ASTM D412	125 psi Min	861.8 kPa Min
Elongation	ASTM D412	150 % Min	150 % Min
CD after Oven Aging	ASTM D1056	30% Max	30% Max
Fluid Immersion	ASTM D1056	150% Max	150% Max
Flammability	FMVSS-302	Pass @ .040" or Thicker	
Service Temperature	-40 to 250 F		

UL Listings ¹	
Gasket and Seals	UL157, UL508, UL157, UL50E
Flammability	UL-94 HF-1

¹ Contact customer service for specification inquiries and UL Information.

Disclaimer: This information is furnished as a guide for selecting materials. Rubberlite Inc. makes no warranties, expressed or implied, of merchantability with respect to the goods or that such goods are fit for any particular purpose. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.