

## Typical Properties of **PLASTAZOTE® HD80**

Polymer	Crosslinked Polyethylene		
Physical Property	Test Method	Result (US Units)	Result (Metric Units)
Density	ISO 7214	5 pcf	80 kg/m <sup>3</sup>
Compression Deflection 25%	ISO 7214	70.2 psi	484 kPa
Compression Deflection 50%	ISO 7214	84.8 psi	585 kPa
Compression Set 50%	ISO 7214	10%	10%
Tensile Strength	ISO 7214	277.4 psi	1913 kPa
Elongation	ISO 7214	90%	90%
Tear Strength	ISO 8067	53.3 lb/in	9338 N/m
Flammability	FMVSS-302	Pass @ 0.118" or Thicker	
Service Temperature	-94 to 257F		

Contact customer service for specification inquiries.

*Disclaimer: This information is furnished as a guide for selecting materials. Rubberlite Inc. makes no warranties, expressed or implied, of merchantability with respect to the goods or that such goods are fit for any particular purpose. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.*